ZD
PRIDE

U. S. NAVAL AMMUNITION DEPOT
CRANE, INDIANA

DEPARTMENT OF THE NAVY
BUREAU OF WEAPONS

JUL 2 2 1963

102

U. S. NAVAL AMMUNITION DEPOT
Crane, Indiana

RDTR No. 114
13 June 1968

A PRELIMINARY INVESTIGATION OF THE
REACTIVITY OF LEAD DIOXIDE

PREPARED BY _____
WILLIAM RIPLEY, Project Leader

PREPARED BY _____
CHARLES A. LIPSCOMB, Physicist

REVIEWED BY _____
DUANE M. JOHNSON, Research Chemist

RELEASED BY _____
P. J. SMITH, Manager, Concept Development Division

RESEARCH AND DEVELOPMENT DEPARTMENT

TABLE OF CONTENTS

         1. Determination of the reactivity of lead dioxide
         2. Particle size
         3. Burning characteristics exhibited by pressure-time curves
         4. Burning rate of delay bodies
         5. Thermal analysis
         6. Calorimetry
         7. Chemical analysis
         8. Density
         9. X-ray diffraction patterns
        10. X-ray effluorescent spectroscopy

Figure 1. Rate Calorimetry Apparatus for the Determination of the Reactivity of Lead Dioxide

Figure 2. Reactivity Curve of Lead Dioxide from Manufacturer L Lead Dioxide vs. Oxalic Acid-Hydrochloric Acid-Ethanol Reagent

Figure 3. Reactivity Curve of Lead Dioxide from Manufacturer M Lead Dioxide vs. Oxalic Acid-Hydrochloric Acid-Ethanol Reagent

Figure 4. Reactivity Curve of Lead Dioxide from Manufacturer N Lead Dioxide vs. Oxalic Acid-Hydrochloric Acid-Ethanol Reagent

FOREWORD

The effort described in this report was authorized under
AIRTASK A35-532-022/323-1/F008-17-02, Air Launched Pyrotechnic
Development, Chemical Standards (Pyrotechnic Properties),
Work Unit No. 6, and was performed at NAD Crane between June
1967 and May 1968. The investigation of the reactivity of
lead dioxide was carried out at the same time as the similar
work on red phosphorus reactivity, which has already been
reported in NADC RDTR No. 110. Again it should be said that
this report is written at a time in the investigation when the
basic objectives have been reached, although many questions
remain to be answered. Consequently, this is not necessarily
a final report.

ACKNOWLEDGEMENT

ABSTRACT

A study is made of the performance characteristics of lead dioxide specimens from five U. S. manufacturers. Reactivity data is obtained using temperature-time curves, pressure-time curves. and burning rate of delay bodies. The relationship of chemical and physical properties of lead dioxide to its performance in the various tests, and the relationship of the various performance tests to each other, are considered.

A PRELIMINARY INVESTIGATION OF THE
REACTIVITY OF LEAD DIOXIDE

INTRODUCTION

1. Although chemicals used in pyrotechnic compositions are
purchased under appropriate military specifications, which are
supposed to control the chemical and physical properties so that
a degree of consistency can be expected in the performance of
the composition. many practical pyrotechnicians are convinced
from experience that unpredictable variations occassionally
appear in the performance characteristics of these chemical
components. These variations are difficult to document for
several reasons. For one thing, military specifications do
not usually require a performance test to determine the re-
activity of the components, but instead assume that if the
chemical and particle size requirements are met, then the reaction
characteristics will be acceptable. Secondly, variations are
often subtle and may only occassionally become pronounced
enough to cause serious performance changes. Since there are
usually no laboratory control tests available to measure re-
activity, except the quality control tests that are run on the
finished units, it is difficult to determine whether the
process, the chemical components, or the hardware is the source
of the failure. If the chemical components are suspected,
chemical analysis and particle size determination may be rerun
on each component. However, the materials may very well pass
the tests, although one of the materials is actually the source
of trouble, since the specifications tests do not necessarily
reveal reactivity variations.

1

2. Military specifications for chemical components used in
pyrotechnic compositions are necessarily compromises between a
set of ideal properties and the practical limitations of commercial
manufacturing processes. Certainly, the more rigorous the re-
quirements the more expensive is the process needed to meet them.
Furthermore, the "ideal properties" of a material depend upon
its use and indeed may not always be understood. The April 1968
edition of Metal Progress was devoted to a special report en-
titled: "Characterization - Industry's Most Urgent Materials
Problem ......" It is the thesis of this special report that
most materials are so poorly characterized that consumers can-
not tell manufacturers precisely what properties they require.
What are the ideal properties of lead dioxide when it is used
as a component in one of the starter compositions? They are
not really known. Consequently, certain "reasonable" or
minimum requirements are established for purity, contaminants,
and particle size that are a compromise between what the pyro-
technician thinks he needs to make a composition with predictable
performance and what the manufacturer can make at an acceptable
price. There is, of course, a good deal of looseness in this
arrangement. Variations in the chemical components inevitably
appear and, consequently, so do variations in the performance
of the final pyrotechnic item. The variations in the components
may at times be so gross that the component fails to meet the
specification requirements. On the other hand the component may
meet the specification requirement and still introduce an

undesirable variation in the performance of the composition.
At best, formula changes must be made to compensate for the
variation; at worse, the material may be unusable.

3. One way out of this situation is to prescribe additional
requirements for the material over and above the general
specification requirements. Besides increasing the cost of the
material, or running into procurement problems at any cost, the
"additional requirements" needed again may not be known.

4. Another approach could be the development of a per-
formance test for the material. In such a test the reactivity
of the material would be evaluated. Since the reactivity of
the material - that is, the ease and rapidity with which the
material interacts with other materials - depends upon the
totality of all physical and chemical properties, the effect
of variations in the material could be seen even if the causes
were not known.

5. This is the approach that has been used in the study of
various chemical materials which are used in current pyrotechnic
compositions. Variations in the behavior of lead dioxide, which
is a basic component of an important starter composition, have
been suspected from time to time, but no hard data are available
to support this suspicion. Consequently, an investigation of
the reactivity, as well as some of the chemical and physical
properties, of lead dioxide has been undertaken.

3

BACKGROUND

1. One of the traditional starter compositions used in con-
junction with red phosphorus flare compositions is based on the
reaction between crystalline silicon, lead dioxide, and cupric
oxide. Various proportions of these three components have
been used in different applications; and, on occassion, changes
in the formula have resulted from unexpected changes in burning
characteristics that have contributed to malfunctions.

2. Formerly the Mk 25 Mod 2 Marine Location Marker employed
a starter composition consisting of 5 parts by weight of lead
dioxide, 6 parts of cupric oxide, and 7 parts of silicon which
we will designate 5L-6C-7S. This formula apparently worked well
for awhile, but malfunctions due to failure of ignition or ex-
cessive delay times finally forced a change to a less energetic
system consisting of 2 parts by weight of lead dioxide, 3 parts
cupric oxide and 5 parts silicon, or 2L-3C-5S. In March 1962,
the Quality Evaluation Laboratory conducted a statistically
designed experiment on the Mk 25 Marine Location Marker. The
first experiment investigated eight factors at three levels
involving the performance of 505 specially prepared units. One
of these factors was the formula and one of the levels was the
formula 2L-3C-5S. In May 1962 a follow-up experiment was con-
ducted involving three factors, one of which was formula. This
time 80 signal units were prepared and tested. One of the con-
clusions of these two statistically designed experiments was that

4

the 2L-3C-5S formula was superior in performance to the 5L-6C-7S formula. In other words, the formula that burned slower, developed less pressure, and had a lower calorific output was superior in performance to the more energetic formula. However, it was not explained why the 5L-6C-7S formula that had once functioned satisfactorily had lately begun to burn too energetically. On the basis of these difficulties an investigation was begun by W. Ripley in April 1963 to elucidate the factors that determined the behavioral characteristics of this family of starter compositions. The results of this investigation were subsequently published in March 1964 as RDTR No. 41 (1). During this investigation a performance test was used which utilized the pressure-time curve obtained when the starter composition burned in a closed vessel equipped with a transducer and a recorder. This test led to the discovery of an unusually reactive silicon specimen that otherwise met the specification requirement and resembled normally reactive silicon specimens in all other properties studied except one - effluorescent spectroscopy revealed the existence of traces of manganese and chromium in the energetic silicon. Since this investigation was done. more burning rate problems have been encountered with the 2L-3C-5S starter composition formula. This time suspicion has fallen upon all of the chemical components, and particularly upon the lead dioxide.

3. Lead dioxide was first prepared by Scheele in 1774 by

RDTR No. 114

treating red lead with chlorine, and soon afterwards by Priestly
who treated red lead with nitric acid (2). Lead dioxide also
exists in the natural state as the mineral plattnerite. It is
manufactured industrially by various methods (3). It may be
prepared by dissolving lead monoxide from red lead (Pb_3O_4) with
dilute nitric acid. It may be obtained from divalent lead salts
such as lead acetate by oxidation with calcium hypochlorite. Or
it can be prepared by electrolyzing a sodium chloride solution
in which lead monoxide is suspended. From the variations re-
ported in such properties as the density and the decomposition
temperature, it is reasonable to assume that the characteristics
of the product are influenced by the nature of the starting
material and by the nature of the manufacturing process.

4. Native lead dioxide occu.s in Idaho and Scotland as a
fine crystal with a gray-black color and a brown streak.
Manufactured lead dioxide varies in color depending to some
extent on the particle size. Finer particle material appears
more reddish. Densities reported in the literature vary from
7.0 to 9.4 g/cc. (2) Remy reports the X-ray density to be 9.42
g/cc. (3) The crystal structure is said to be the same as that
of tin dioxide which is usually tetragonal but may also exist
in the rhombic and hexagonal forms. (2) Native crystals of lead
dioxide are tetragonal with a reported axial ratio of <u>a:c</u> being
1:0.6764. (2) On the other hand, samples of lead dioxide pre-
pared in the laboratory by Ferari were tetragonal with <u>a</u> being
4.984°, <u>c</u> being 3.40A° and the axial ratio <u>a:c</u> being 1:0.682. (2)

6

Copies of ASTM powder diffraction data cards for lead dioxide are
shown in Table XI.

    5.   According to J. Heyes, the structure of lead dioxide is
represented with divalent lead and oxygen attached to a quad-
rivalent oxygen atom: (2)

$$Pb = 0 = 0$$

But A. Colsen showed that the lead is quadrivalent and suggested
the structure:

$$0 = Pb = 0$$

L. Marino argued that the lead is quadrivalent, and that one or
both of the oxygen atoms are also quadrivalent. The unsymmetrical
formula for the oxide, shown below on the left, is preferred
because the lead sulfite obtained by reducing the oxide with
sulfur dioxide is unsymmetrical: (2)

Pb $\diagup\!\!\!\!\!\diagup$ 0   Pb $\diagup\!\!\!\!\!\diagup$ 0
$\diagdown$ 0 $\diagdown$ 0

Marino also assumed that lead dioxide can exist in both single
and double molecules: (2)

Pb $\diagup\!\!\!\!\!\diagup$ 0   0 $\diagup$ Pb $\equiv$ 0 $\diagdown$ 0
$\diagdown$ 0 $\diagdown$ Pb $\equiv$ 0 $\diagup$

It was formerly believed that there is a pseudo-cubic phase of
lead dioxide represented as $PbO_{1.87}$. However, Katz has shown
that this new phase is characterized by the composition
PbO_2 .x PbO in which x varies from 0.75 to 2. (2) This composition
is not to be understood as a mechanical mixture, but as a solid

solution of PbO_2 and PbO_1.

6. According to Mellor lead dioxide is decomposed when exposed to light, forming red lead and oxygen: (2)

$$3\ PbO_2 \longrightarrow Pb_3O_4 + O_2 \uparrow \qquad \text{Equation 1}$$

Moderate heat is said to decompose lead dioxide to red lead and strong heat to decompose it to red lead and oxygen. (2) The existence of lead sequioxide, Pb_2O_3, is supported by some and discounted by others. According to Remy Pb_2O_3 is not formed during the thermal degradation of PbO_2. However, the existence of other oxide intermediates between PbO_2 and PbO is accepted, although they have not yet been characterized. (3)

7. Lead dioxide is a powerful oxidizer. It inflames if triturated with sulfur or red phosphorus. (3) When warmed with concentrated sulfuric acid, it evolves oxygen; with concentrated hydrochloric acid it evolves chlorine. As already noted above, it 's unstable to light and heat. In pyrotechnics it is used with such fuels as silicon and boron, and even zirconium metal. The obscurity of its structure and composition, the variations in its physical and chemical properties, and the lack of information on the correlation between structure, composition, and properties, indicate that further characterization of the material and its behavior are required.

OBJECTIVES

1. The present investigation has had six principal objectives:

a. To find laboratory methods of measuring the reactivity, or the reaction rate, of lead dioxide, and ultimately

of other pyrotechnic chemicals.

b. To compare and correlate when possible reactivity results obtained from different methods of determining reactivity.

c. To investigate a quantitative relationship between the average particle size, the surface area, and the reactivity of lead dioxide.

d. To determine which method of measuring the particle size is more valid in predicting the reactivity of lead dioxide.

e. To determine if other factors besides the average particle size or surface area affect the reactivity of lead dioxide.

f. To determine the variations in reactivity that exist in lead dioxide currently used in production, and in lead dioxide from different sources.

EXPERIMENTAL RESULTS

1. Determination of the reactivity of lead dioxide

a. A laboratory test method for determining the reactivity, or the reaction rate, of a solid material like lead dioxide must necessarily be a destructive test. The lead dioxide is attacked by some chemical agent, and in the process of the ensuing reaction the lead dioxide is destroyed. The rate at which the lead dioxide is destroyed is somehow measured and recorded, and this rate is assumed to be related to the reactivity of the lead dioxide.

b. Since the lead dioxide must react with another substance, three general modes of reaction are possible: the

9

lead dioxide can react with a gas, with a liquid, or with a solid.
While all three of these modes are currently under study, this
report is mainly concerned with a study of the reaction of solid
lead dioxide with a liquid reactant, and with the burning
characteristics of certain solid-solid systems.

c. Lead dioxide is dissolved by many liquid chemical
reagents. If we obtain a temperature-time curve of the reaction
between lead dioxide and some liquid reactant under isothermal
conditions, two requirements must be satisfied in choosing a
reactant: sufficient heat must be generated and the reaction
must not proceed either too rapidly or too slowly. Reactions
with hydrogen peroxide and hydrochloric acid proved to be too
rapid, while the reaction with oxalic acid was slow and developed
little heat. A reagent was finally developed, based on an al-
coholic solution of oxalic and hydrochloric acids, which gave a
satisfactory time-temperature curve. The oxalic acid solution
was prepared fresh each day by adding 120 grams of anydrous
oxalic acid and 60 ml of distilled water to a one liter volumetric
flask and bringing the solution to the mark with 95% ethyl
alcohol. Just before using the reagent, 5 ml of 12N hydrochloric
acid was added to 45 ml of alcohol-water solution of oxalic
acid. This mixture was at once cooled in an ice bath to 23°C
and immediately added to the reaction vessel containing the lead
dioxide sample.

d. The apparatus used, which is basically a rate
calorimeter, is shown in Figure 1. Essentially, it consists of

NaN

a Dewar reaction vessel equipped with a glass stirrer, a funnel for addition of reagent, an inconel-sheathed chromel-constantan thermocouple probe (1/16" O. D.), a cold junction compensator, and a strip chart recorder. The response time of the thermocouple probe was 0.5 seconds over the temperature range of the reaction.

e. In a typical run 4.00 grams of lead dioxide was weighed out on a triple beam balance accurate to 0.01 grams and carefully introduced into the Dewar flask. The temperature of the room was maintained at 23-25°C. 50 ml of the reagent was freshly prepared by mixing 45 ml of alcoholic oxalic acid solution and 5 ml of 12N hydrochloric acid. The reagent was immediately cooled in an ice bath to 23°C and added to the reaction vessel. The stirrer was started at approximately 6 revolutions per second. Different chart speeds and millivolt ranges were required for different lead dioxide samples. More reactive specimens were run at 2.5 mv and 4 in./min. and less reactive specimens were run at 1.25mv and 1/3 in./min.

f. The reaction mechanism of this system is somewhat complex and is probably represented by the following equations:

$$PbO_2 + H_2C_2O_4 \longrightarrow PbO + H_2O + 2CO_2\uparrow + \Delta H \qquad \text{Equation 2}$$
$$PbO + 2HCl \longrightarrow PbCl_2\downarrow + H_2O + \Delta H$$

$$PbO_2 + 4 HCl \longrightarrow PbCl_2 + 2 H_2O + Cl_2\uparrow + \Delta H \qquad \text{Equation 3}$$

g. Commercial lead dioxide specimens were obtained from five different manufacturers. In order to study the relationship

11

between the particle size and the reactivity, the five specimens
were fractionated by sedimentation and liquid elutriation.
Separation using distilled water was relatively easy on the large
particle specimens, but on the small particle specimens separation
was difficult at best. This difficulty in obtaining relatively
coarse and fine fractions indicates a limited particle size
distribution as well as the limits of the fractionating technique
itself.

h. Figures 2 - 6 show reaction rate curves for the five
parent samples of lead dioxide. In these curves temperature is
indicated on the Y coordinate and time on the X coordinate.
Figure 7 shows the reaction rate curves plotted on the same scale.
Figures 8 - 10 show reaction rate curves of three fractions
obtained from Manufacturer O. All of these curves reveal the
rate at which heat is generated when lead dioxide reacts with
an excess of alcoholic oxalic acid-hydrochloric acid reagent.
Table I shows the dimensions and properties of the reaction
rate curves for all the parent samples as well as the fractions
obtained from them. Figure 11 shows the reciprocal of the average
particle diameter plotted as a function of the tangent of the
inflection point of the individual reaction rate curves. Figure
.2 shows the reciprocal of the average particle diameter
multiplied by the reciprocal of the absolute density plotted
as a function of the tangent of the inflection point of the
individual reaction rate curves.

12

i The temperature-time curves obtained from exothermic reaction of lead dioxide with alcoholic oxalic acid-hydrochloric acid solution are sigmoid type curves. This type curve is characteristic of autocatalytic reactions, although it has not been definitely demonstrated that the reaction is in fact autocatalytic. The inflection point of each curve has been chosen to characterize the reaction rate of the individual sample, since at this point the rates of the two competing processes - autocatalysis which increases the rate process versus depletion of lead dioxide which slows the rate process - are at equilibrium. The rate of reaction at the inflection point is expressed as the value of the slope at that point. When the values obtained for the slope at the inflection point are plotted against the reciprocal particle diameter for each of the lead dioxide parent specimens and its fractions, linear relationships are obtained. The individual slopes for each of the five lead dioxide specimens obtained from U. S. Manufacturers are shown in Figure 11. The wide range of values for the different slopes is an indication of the variations in the reactivity of the different lead dioxide specimens. For example, lead dioxide samples furnished by Manufacturer L and Manufacturer P have comparable particle sizes and yet they stand at the opposite extremes in terms of reactivity. The reaction rate of the specimen from Manufacturer P is in the range of 19 times as fast as that of Manufacturer L. Moreover, the heat energy released from the different specimens is not

13

the same. The temperature rise shown by the peak height of the curve is about 50% greater for specimens M, N, and P than for specimens L and O, necessitating that they be recorded on a higher millivolt range and at a faster chart speed. A higher heat of reaction indicates a different internal energy and therefore a different composition or structure. The linear plots shown for each of the lead dioxide specimens in Figure 11 can be represented by the equation:

$$\left.\frac{dT}{dt}\right|_{t\,=\,t_i} = \frac{K}{d} \qquad \text{Equation 4}$$

Where t_i equals the lapsed time at the point of inflection, $\frac{dT}{dt}$ equals the rate of temperature increase, d equals the average particle diameter, and K equals a proportionality constant. Values for K are shown in Table II.

    2. Particle size

        a. The average particle size of the five parent lead dioxide samples was determined by the air permeability method using the Fisher Sub Sieve Sizer. The density obtained experimentally by the pyconometer was used instead of the value of 9.38 g/cc given in most reference books. (A) Values are shown in Table III.

        b. The surface area of the phosphorus samples was studied by the nitrogen adsorption method. A Numinco-Orr

Surface Area - Pore Volume Analyzer, Model MIC-103, shown in
Figure 13, was used. A quantity of sample was weighed out ap-
proximately and placed in the sample tube to give a total
surface area between 1 and $10m^2$. The sample tube containing the
sample was then attached to the instrument and degassed for
15 hours at 100°C and under a vacuum of 1 micron of mercury.
Dry helium gas under liquid nitrogen was used to measure the
dead space volume before the adsorption measurement. Nitrogen
gas under liquid nitrogen was used as the adsorbate during the
actual tests. Several pressure readings, which were indicative
of the amount of nitrogen adsorbed, were taken in each test.
The sample was then reweighed to an accuracy of 0.001g. Cal-
culations were based on the area occupied by a single nitrogen
molecule, which is $15.8 \overset{\circ}{A}{}^2$. Points were calculated from the
pressure readings and plotted on graph paper. From the slope
and intercept of the best straight line through the data points,
the specific surface area, Sg, was found.

　　　c. A comparison of the specific surface area, Sg, and
the average particle diameter for five parent samples of lead
dioxide and four fractions of one of the parent samples (Sample
O) is shown in Table IV. Inconsistencies between values for
the APS and values for the surface area are evident: e.g., the
APS of Sample L is 2.15 u with a surface area of .59 m^2/g, while
the APS of Sample P is 2.10u and the surface area is 3.72 m^2/g.

15

Also it can be seen in Figure 7 that the two groups of lead
dioxide samples are determined by their surface areas and not
their average particle diameters. Obviously, this is an instance
in which the average particle diameter is not a function of
surface area and where the surface area is the true property
that relates to the reactivity.

3. Burning characteristics exhibited by pressure-time curves

a. Since late 1963 the performance of the 2L-3C-5S
starter composition used in the Mk 25 and Mk 58 Marine Location
Markers has been evaluated on the basis of its pressure-time
curve. This pressure-time curve is obtained by combusting 12
grams of the starter composition in a closed vessel which is
equipped with a transducer and a recorder. The apparatus and
the procedure have been described in RDTR No. 41. Based on
this study an acceptable range of burning characteristics for
the Mk 25 Mod 2 starter composition was determined. Figure 14
shows the pressure-time curve for a typical starter composition
obtained during that study. Three properties of the curve were
used to characterize the burning performance of the composition.
The burning rate, θ, is obtained by finding the angle of the
slope of the curve at $t\frac{1}{2}P_{max}$, that is, the time at which one-half
of the maximum pressure is attained. The accepted range for
the angle θ was chosen on the basis of experience to be 55° to
68°. The maximum pressure, P_{max}, was assigned a value of 6.75-
9.65 psi. The time required for the pressure to reach its

maximum value, t P_{max}, was assigned a range of 6.1-7.9 seconds. Again, there was no inner necessity about these performance requirements. They were selected as reasonable values based on the performance of a great number of production batches tested over several months. While this method was useful in evaluating the burning characteristics of the starter composition, no rigorous analysis of the significance of the pressure-time curve was performed at that time, or has been performed since. And although various factors which affect the pressure-time curve-- composition, particle size, moisture, contaminants, crystalline modifications--were investigated, undesirable variations that eluded explanation have to appear from time to time.

b. Although the problem of a standard oxidizer and a standard fuel has not yet been solved to the satisfaction of everyone, some reproducible variations can be found among starter compositions made with the same silicon and cupric oxide but with different specimens of lead dioxide. Figures 15-24 show pressure-time curves of 2L-3C-5S starter composition made from ten different lead dioxide specimens obtained from six U. S. manufacturers. Table III shows the values for the burning characteristics of a total of 13 specimens from these six manufacturers--the ten of which pressure time curves are shown are included--along with other physical and chemical characteristics.

17

c. Altogether, this data presents a baffling picture
of contradictions and inconsistencies. While the pressure-time
curves obtained on a single specimen are fairly reproducible,
there are still some individual runs that are far beyond the norm,
indicating that variations do exist in the procedure itself.
However, any attempt to relate the physical and chemical properties
of lead dioxide that were investigated during the course of this
work to the burning characteristics shown by the pressure-time
curves appears to be futile. Take particle size, for example:
there is no discernible correlation between the tangent of θ and
the reciprocal of the average particle diameter. Inspection of
Table III will show that specimens with small average particle
diameters are sometimes relatively fast burning and sometimes
relatively slow burning. The smallest specimen with an APS of
0.32u is comparable in burning rate with specimens having APS
values of 0.51u and 1.65u. This lack of pattern or trend is all
too clearly shown by the scatter of points in Figure 25, where
tan θ is plotted versus the reciprocal of the average particle
diameter. Nor is there any discernable correlation between the
absolute density or the apparent density and the burning rate.
Specimen L-1 with the highest absolute density has the high
value for the angle θ of 61°; but specimen Q with the second
highest absolute density has one of the lowest values for the
angle θ, 42°. This same lack of correlation also exists between
the apparent density and the burning rate. Nor is their any

18

obvious relationship between the purity and the burning rate.

Sample N-2 assayed 79.5% PbO$_2$, which is about 15% below the

minimum specification requirement of 95%. Yet it burns

relatively fast - Θ is 64° and the maximum pressure is 8.6

psi - while the two slowest burning samples have purities above

96%. All this indicates that some other factor or group of

factors outside those considered in this investigation determine

the burning rate. This data also suggests that the military

specification requirements of lead dioxide have little or no

correlation with the burning characteristics of the starter

composition of which the lead dioxide is an important component.

    4. Burning rate of delay bodies

        a. The inconclusiveness of the pressure-time curve study

made it desirable to investigate further the burning rate of solid-

solid lead dioxide compositions. Consequently, it was decided

that the burning time of delay bodies which normally utilize a

lead dioxide composition should be investigated. This composition

is prepared by screening together 85.1% lead dioxide and 10.6%

boron. After the mixture has been screened three times, it is

combined with 4.3% viton which has been dissolved in acetone

so that the resulting solution is 16% viton. The mixture is

worked until it is almost dry and then it is screened through

a No. 16 U. S. Standard Sieve and finally through a No. 30

U. S. Standard Sieve. It is then pressed in 500 mg increments

into a 1" x 1/4" I. D. aluminum delay body under a dead load of

1000 lbs.

b. The burning rate in grams per second of ten lead dioxide specimens from five U. S. manufacturers is shown in Table V. Also the weight of composition that could be pressed into the 1" x 1/4" I. D. aluminum delay body is shown, as well as the burning time per inch. It can be seen that the burning rate varies from 2.97 g/sec for specimen P to 5.19 g/sec for specimen N-4. It is of passing interest to note that this specimen with the fastest burning rate in a delay composition exhibited the slowest burning rate on the pressure-time curve. Furthermore, it can be seen that the weight of the delay composition which could be pressed into the body varies from 3.850 grams for Specimen L to 3.000 grams for specimen N-1. Thus it would appear that there is a correlation between the average particle diameter, the apparent density, and the absolute density of the lead dioxide specimens, and the loaded density of the composition.

c. Figure 26 shows the plot of the burning rate in g/sec versus the reciprocal of the product of the absolute density and the average particle diameter. Figure 27 shows the plot of the burning rate in g/sec versus the reciprocal of the product of the apparent density and the average particle diameter. Figure 28 shows the plot of the burning rate in g/sec versus the reciprocal of the average particle diameter multiplied by the sum of the reciprocals of the apparent density and the absolute density. The fact that the wide differences shown in

Figure 26 become much less pronounced in Figure 28 indicates that the difference in burning rates of the various lead dioxide-boron delay compositions depends almost entirely upon the average particle diameter, the apparent density, and the absolute density of the lead dioxide specimen used in the delay composition.

5. Thermal Analysis

a. Differential thermal analysis was performed on samples of lead dioxide obtained from six domestic manufacturers. Values for the endothermic peaks are shown in Table VI and typical thermograms of lead dioxide samples from the different manufacturers are shown in Figures 29 to 34. From this data it can be seen that the decomposition mechanism varies for the different samples. For Sample L decomposition begins at about 400°C and peaks at 465°, 512°, and 645°C. This thermogram shows a characteristic curve which is not quite like the curves of any of the other lead dioxide samples. For Sample M decomposition begins at about 350°C and peaks at 417°, 458°, and 640°C. Again the material has a characteristic curve. Decomposition of Sample N begins at 350° and peaks at 420°, 455°, and 610°C. The curve of the material has the same pattern as that of Sample M. Decomposition of Sample O begins at 350°C and peaks at 450°, 458°, and 615°C. The material has a characteristic shape that is unlike curves of the other materials. Decomposition of Sample P begins just above 300°C and peaks at 435°, 480°, and 605°C. This is the first sample to exhibit four distinct and almost

21

equal endothermic peaks. Again its curve has a characteristic
shape. For Sample Q decomposition begins at about 350°C and
peaks at 448°, 490°, 535°, and 610°C. Again there are four
peaks, indicating that the decomposition mechanism of Sample Q
is the same type as Sample P, although it possesses individual
characteristics. According to DTA curves of thermal decomposition
two general types of decomposition patterns are indicated, with
samples showing individual characteristics within these two
types. The first type has three distinct peaks, the first two
peaks merging while the third peak is distinctly apart. In
the second type there are four peaks of about the same height.
The four peaks are distinct and separate in Sample P while in
Sample Q the first three peaks merge. The temperature at which
decomposition begins varies among the different samples from
about 300° to 400°C.

   b. Differential thermal analysis was also performed on
a 2:1 composition of lead dioxide and sulfur. This was to
determine any differences in reactivity which might be revealed
in a reaction between the various lead dioxide samples from
six U. S. manufacturers and a relatively reactive fuel like
sulfur. Endothermic and exothermic peaks for the different lead
dioxide samples are shown in Table VII. Representative
thermograms for lead dioxide from each of the six manufacturers
are shown in Figures 35 to 40. Lead dioxide from Manufacturer
L shows a sharp exothermic peak at 303°C which indicates ignition

22

but not·explosive ignition. (Figure 35) Sample M showed two kinds of ourves (Figure 36), one in which explosive ignition ocourred at 125°C and the other in which explosive ignition ocourred at 220°C. This same pattern of activity is also shown in Samples N and P. (Figures 37 and 39). Samples O and Q show similar activity pattern (Figures 38 and 40).

    c. These thermograms show pre-ignition reactions associated with the melting point of sulfur (110°C). With samples M, N, and P ignition was a result of the reaction that started with the melting of the sulfur. However, this reaction does not always result in ignition even with different runs on the same sample. On the other hand, no runs of samples L, O, and Q ignited at this point, and the general conclusion is that these samples are less reactive. Another pre-ignition reaction is seen beginning at about 200°C in those samples that did not ignite after the sulfur had melted. This temperature is not associated with any particular changes that appear in the DTA thermograms of either sulfur or lead dioxide. However, a major exothermic reaction begins at about this temperature and culminates in a peak at 303°C for sample L-1, at 310°C for sample P, and at 295°C for sample Q. This same PIR culminates in ignition for sample M-2 at 220°C, and in ignition for sample O at 310°C. From these results it can be said that samples L and Q are definitely less reactive than the other samples under these test

23

conditions since they are the only samples that did not undergo rapid propagative ignition. Otherwise, in general, the results of these tests do not indicate clear and consistent differences in the behavior of the various lead dioxide samples.

6. Calorimetry

a. Calorific values for the heats of reaction of 2L-3C-5S starter compositions made from the various lead dioxide samples obtained from the six domestic manufacturers are shown in Table III. It can be seen that values range from 372.44 cal/g for sample O to 353.34 cal/b for sample N-2. It can be seen from the results given in Table III that large variations in ʼhe purity of the lead dioxide used in the starter compositions do not show correspondingly large variations in the caloric value of the compositions. Sample N-2 assays at 79.5% PbO_2 - 15.5% below the minimum specification requirement - and yet it shows barely a 2% decrease in calorific output from other samples (N-4 and P-1) that assay about 96% PbO_2. Moreover, this low purity does not particularly affect the other performance tests in an adverse way: the pressure-time curve is fast and the delay burning rate average. Thus the relation between the performance and the purity is anything bur clear. Indications are that factors more important than the PbO_2 assay dominate the performance of the compositions.

b. Calorific values for the heats of reaction of different ratios of lead dioxide and silicon are shown in Table VIII.

24

From this table Figure 41 was obtained in which the enthalpy
is plotted as a function of the percent of the silicon fuel.
The enthalpy, q, is equal to the heat per mole of available
oxidizer; or

$$g = \frac{\Delta H \text{ X molecular weight of oxidizer}}{\text{weight of composition X percent of oxidizer}}$$

where Δ H is the calorific value of the fuel-oxidizer combinations
shown in Table VIII. Figure 41 indicates still another way of
demonstrating inherent differences in the lead dioxide samples.
At the stoichiometric point of about 18% silicon, the enthalpy
varies from approximately 13.5 K-cal/mol for sample N to 15.0
K-cal/mol for sample P, a variation of almost 10%.

    7.   Chemical Analysis

        a.   Chemical analysis was performed upon 13 lead dioxide
samples from six domestic manufacturers. The results of the
chemical analysis is shown in Table IX. The purity as % PbO_2
was obtained according to the method described in MIL-L-376B
for lead dioxide, technical. This method is based on the
assumption that only PbO_2 in the sample will decompose hydrogen
peroxide in dilute nitric acid, whereas in fact various con-
taminants might also decompose hydrogen peroxide. The samples
analyzed exhibited a wide range of values for purity, from
79.5% for sample N-2 to 98.1% for sample Q. More than half of
the samples, however, would not have passed the minimum re-
quirement of 95% imposed by the specification. The percent of
lead was determined gravimetrically as lead chromate.

8. Density

a. Densiti'.; of lead dioxide samples from 7.0 to 9.4
g/oc have been reported in the literature. Absolute densities
of nine lead dioxide samples from six manufacturers are shown
in Table III. Values range from a low of 6.82 g/cc for sample
N-1 to 9.28 g/oc for sample L-1. The relationship between the
density, the structure, and the reactivity is not fully under-
stood. Bur in general higher density is associated with lower
reactivity.

b. The apparent density of 13 samples from six
manufacturers is also shown in Table III. These values vary
from a high of 2.83 g/oc for sample 0 to a low of 1.36 g/oo
for sample N-3. The apparent density is determined by filling
a 100 ml graduated cylinder that has been cut off at the 100
ml mark with lead dioxide that is slowly sifted into the cylinder
through a powder funnel. The effect of the apparent density of
lead dioxide on the packing desnity of a boron-lead dioxide delay,
and consequently on its burning rate, has already been discussed
in the above section on the burning time of delay bodies.

9. X-ray Diffraction Patterns

a. X-ray diffraction patterns were obtained on lead
dioxide samples from five manufacturers using nickel filtered
Cu-Kα radiation. While no major differences were found, it
does appear - as can be seen from the presence of a small peak
at 3.12 ± 0.02A° in Table X - that small amounts of α-PbO_2
are present in samples N, 0. and P, which are otherwise pre-

26

dominately β -PbO$_2$.

10. X-ray Effluorescence Spectroscopy

a. X-ray effluorescence spectroscopy was performed on lead dioxide samples from five manufacturers revealing only a strong Pb peak.

CONCLUSION

1. The study of materials is ultimately the study of the complex interrelationship between properties, composition, structure, and energy state. These are all merely aspects of a larger whole. A substance has certain properties because of its composition, structure, and energy state.

2. Traditionally, substances have been characterized by their chemical composition (based on a partial rather than an ultimate analysis) and by their physical particulate state. In the course of this work we have adopted an alternate approach to the characterization of substances. Substances have been characterized by their behavior under a given set of conditions. If they behave differently, it has been assumed that they are different; if they are different, then some of their measurable properties must be different.

3. Lead dioxide was among the substances chosen for this study because reports on its structure and properties vary and because its behavior as a pyrotechnic component has more than once come under suspicion. Variations in its density from 7.0 to 9.4 g/cc have been reported in the literature and

27

similar variations have been found in this study. The color of
commercial lead dioxide varies from red-brown to almost black
while its particle size varies from approximately 0.3u to
approximately 2.4u. The particle size distribution, as evidenced
by the difficulties encountered in fractionating the powdered
material, also varies from sample to sample, with some materials
such as sample O showing a considerable range of particle size,
while others such as sample N-3 showing almost no range at all.
Based on x-ray diffraction patterns, two types of lead dioxide
- α-PbO$_2$ and β - PbO$_2$ - have been reported, although all of the
samples studied during this investigation were fundamentally
β -PbO$_2$. Differential thermal analysis indicates that there
are two distinct types of decomposition mechanism shown by the
various lead dioxide samples, one characterized by three
endothermic peaks and the other characterized by four endo-
thermic peaks. The heat of reaction of 2-3-5 starter composition
made from the various lead dioxide samples varies from 372.4
cal/g to 353.3 cal/g. Chemical analysis utilizing the hydrogen
peroxide - lead dioxide reaction indicates that the purity of
the samples varies from 79.5% PbO$_2$ to 95.9% PbO$_2$. Similarly,
the performance and reactivity tests indicate significant dif-
ferences in the behavior of the various lead dioxide samples.

4. These measurements of properties and performances raise
two immediate questions: first, is there any correlation between
the various performance tests, e.g., is the same material
always the fastest reacting in all of the tests; and secondly,

28

is there any correlation between the properties of the lead
dioxide samples and their performance?

5. Figure 7 shows that the temperature-time curves of the
lead dioxide samples fall into two distinct groups. The data
on specific surface area in Table IV shows that these two groups
depend upon the surface area of the lead dioxide samples. For
example, samples L and O which make up the slow reacting group
have surface areas of 0.6 m^2/g and 0.96 m^2/g respectively,
while samples P, M, and N which make up the fast reacting group
have surface areas of 3.72 m^2/g, 4.35 m^2/g, and 4.94 m^2/g
respectively. For four of these samples the reaction rate
constant is a linear function of the surface area, as shown in
Figure 42. However, sample P does not fit into this linear
relationship, indicating that its reaction rate constant is
influenced by some other factor in addition to the specific
surface area. Moreover, the value of the average particle diameter
of sample P, 2.38u, is very poorly related to the surface area,
3.72 m^2/g, and to the reaction rate of the sample in a
liquid medium. This is an important instance where the apd is
entirely misleading as a factor in determing the reactivity,
which is in fact related to the surface area. One can only
speculate concerning the reason for the large descrepancy between
the value given by the Fisher Sub Sieve Sizer and the value
given by the Surface Area Meter. The particles apparently have
a large internal area and may resemble porous balls.

29

6. If we turn now to the reaction rates of these five
specimens in solid-solid reactions - in this case as components
in a delay composition - we find little resemblance between the
burning rates and the reactivity rates shown in Table III. In
the delay burning rates, sample P is the slowest, and samples
M, N, and O are the fastest. Not much resemblance to the clear
out division of groups shown in Figure 7. The slopes of the
lines in Figure 26 indicate the order of increasing rate of
reaction to be N, O, P, L, M with a loose grouping of N and O
as the slowest and M, L, and P as the fastest. In Figure 27 where
the burning rate in a delay body is plotted against the re-
ciprocal of the average particle size times the apparent density
(instead of the absolute density as in Figure 26) the lines
draw together somewhat and the groupings change. Now the order
of increasing reaction rates are P, L, O, N, and M, with M and
N forming one group and O, L, and P another. However, in Figure
28 where the effects of particle size ($\frac{1}{d}$), absolute density
($\frac{1}{\rho_{abs}}$), and apparent density ($\frac{1}{\rho_{apt}}$) are all taken into
account, the lines draw even closer together and the slopes of
the lines fall once again into two distinct groups, M, P, and N
forming the slower group and O and L the faster group. Two
things are remarkable about this. The first is that the samples
fall into the same groupings that were shown in the liquid
reaction in Figure 7: L and O in one group and N, P, and M in
the other. In other words, when the effects of the average

30

particle size, apparent density, and absolute density are
normalized - effects that dominate the burning characteristics
in a delay - the original groupings based on reactivity in the
liquid reagent are restored. The second remarkable thing is
that the order of increasing reactivity is almost exactly
reversed. Sample L, the slowest in Figure 7, becomes the fastest
in Figure 28. In the liquid reaction the order of <u>increasing</u>
reaction rates was L, O, N, M, and P; in the delay burning rate
the order of <u>decreasing</u> reaction rates is L, O, N, P, and M.

7. If this is indeed true, as it certainly seems to be, it
suggests a number of interesting possibilities. It indicates
differences of "reactivity" exist over and above differences
in purity, particle size, or surface area. It indicates that
the reactivity differences may be covered over and obscured
because one test is responsive to one set of factors while a
second test may be responsive to a second set of factors. And
it indicates that differences in reactivity can be seen in
different types of tests in which the reaction rate of a series
of samples may be reversed.

8. The reactivity results shown in Figure 7, in which
powdered lead dioxide reacts with a liquid reagent in which
it is suspended, are almost exactly reversed in Figure 28, in
which lead dioxide is mixed with boron (and a viton binder) and
pressed into a delay composition. And furthermore, the order
and magnitude of the reactivities of the five lead dioxide
samples undergo changes from Figure 26 to Figure 27 and finally

31

to Figure 28. We have already suggested an explanation for this
second phenomenon. The delay burning rate is largely dependent
on properties that affect the packing density--the particle size,
the absolute density, and the apparent density. On the other
hand, the reaction rate of lead dioxide in acid solution is
largely dependent on the surface area and little affected by
the packing density. So we see that factors that may heavily
affect the rate of reaction in one set of conditions may have
little effect on the rate of reaction in another set of conditions.
And indeed the properties that cause lead dioxide to react
rapidly in solution--that is, the particle size and more directly
the surface area--cause it to react more slowly in a delay
composition. This is because large particles with a small particle
size range do not pack closely in a delay composition, and the
increased porosity that results causes the composition to propagate
the flame front through it more rapidly.

9. Pressure-time curves are routinely obtained on starter
compositions used in the Mk 25 and the Mk 28 Marine Location
Markers. The starter composition contains lead dioxide in
varying proportions--usually 20% by weight--and the lead dioxide
is a key component since it largely controls the ignitability
and burning rate of the composition. The effect of formula
changes on the pressure-time curves has already been studied in
RDTR No. 41. However, continued variations in the same formula
have not been satisfactorily explained. In the present study,

32

it has been shown that lead dioxide specimens from different manufacturers, used in otherwise identical formulas, give a wide range of pressure-time performance curves. This only confirms what was already suspected. The problem will no doubt continue. Moreover, it must be said that the significance of the pressure-time curve is not well understood. This difficulty is compounded by the fact that there appears to be no correlation between the form of the pressure-time curve and the physical and chemical properties of lead dioxide studied in this investigation. Considerable differences in purity and average particle size, upon which the military specification is based, appear to have no directly discernable relationship with the form of the pressure-time curve. This problem is currently under study.

10. Besides the poor correlation between PbO_2 purity and the pressure-time curve--Table III indicates that sample N-2 has a purity of only 79.5% PbO_2 and yet it has a fast pressure-time curve--there is generally also a poor correlation between PbO_2 purity and the heat of reaction of the starter compositions. For example, sample N-3 has a purity of 85.1% PbO_2 and a caorific value of 357.4 cal/g; sample N-4 has a purity of 96.3% PbO_2 and a calorific value of 360.1 cal/g. This would not appear to be consistent and would indicate that the evaluation of the chemical purity has little relation with the actual oxidizing power of the lead dioxide in a pyrotechnic composition.

FUTURE WORK

1. Since the analytical method of determining PbO_2 is not
highly specific, and since the relationship between the purity
and the heat of reaction and the purity and the pressure-time
curve often appears inconsistent, a re-evaluation of the existing
analytical technique will be initiated. Other test methods will
be explored in an effort to find a procedure that is specific
for PbO_2 or that can distinguish between the various oxides of
lead.

2. An investigation is already underway to elucidate the
form of the pressure-time curve as well as the inter-relationship
between the values of θ, P max, and t P max. Furthermore, the
properties of lead dioxide that cause samples from different
manufacturers to give such different pressure-time curves are
being sought.

3. Finally, other performance tests which may be used to
predict the burning characteristics of lead dioxide in starter
compositions and other pyrotechnic systems will be reviewed.
Also consideration will be given to the concept of specifying
a constant performance value based on a sliding formula, instead
of the present tendency of requiring a rigid formula and a
rigid performance, which is based on the mistaken premise that
all chemical components that pass current specifications are
more or less alike.

LITERATURE CITED

1. Ripley, William L., "Investigation of the Burning Characteristics
of the Lead Dioxide-Silicon Starter Composition," RDTR No. 41,
USNAD Crane, Indiana, 26 March 1964.

2. Mellor, J. W., "A Comprehensive Treatise on Inorganic and
Theoretical Chemistry, Vol XII," 1960, John Wiley & Sons, Inc.,
New York.

3. Reny, H., Treatise on Inorganic Chemistry, Volume I, Elsevier,
New York, 1956.

4. Hodgman. C. D.; Weast, R. C.; and Selby, S. M. ed., "Handbook
of Chemistry and Physics" 42nd Ed., 1961, The Chemical Rubber
Publishing Co., Cleveland, Ohio.

APPENDIX I

FIGURE 1   Rate Calorimetry Apparatus for
the Determination of the
Reactivity of Lead Dioxide

FIGURE 3: Reactivity Curve of Lead Dioxide from Manufacturer X
Lead Dioxide vs. Oxalic Acid - Hydrochloric Acid -
Ethanol Reagent

4.00g Lead Dioxide
45ml Ethanol Oxalic
Acid Reagent
5ml Hydrochloric Acid
Reagent
Chart Speed - 4 in/min.
Range --1.5mv --.50

Temperature, °C

-2.0
-1.5
-1.0
-.5
0

Time, Minutes

FIGURE 4. Reactivity Curve of Lead Dioxide from Manufacturer B Lead Dioxide vs Oxalic Acid -- Hydrochloric Acid Ethanol Reagent

4.00g Lead Dioxide
12ml Ethanol Oxalic
Acid Reagent
5ml Hydrochloric Acid
Chart Speed -- 4 in/min
Range : 2.5mv

Time, Minutes

FIGURE 5 Reactivity Curve of Lead Dioxide from Manufacturer O
Lead Dioxide vs Oxalic Acid - Hydrochloric Acid -
Ethanol Reagent

4.00g Lead Dioxide
45ml Ethanol Oxalic Acid
    Reagent
5ml Hydrochloric Acid
    Reagent
Chart Speed - 1/3 in./min.
Range - 1.25mv

FIGURE 6   Resistivity Curve of Lead Dioxide Cross Reaction Rate ?
Lead Dioxide Vs Cusite mid ?? Equivalents to Acid
Ethanol Reagent

4.00g Lead Dioxide
45ml Ethanol Oxide
Acid Reagent
5ml Hydrochloric Acid
Reagent
Chart Speed - 4 in/min.
Range - 2.5mv

Time, Minutes

FIGURE 7 Reacti / Curves for Lead Dioxide.
Samples from Five Domestic Manufacturers

$4g. PbO_2$ vs. $150ml$ $C_2H_5OH - H_2C_2O_4 - HCl - H_2O$ Reagent

Temperature, °C.

Time, Minutes

45

FIGURE 4: Resistivity Curve of Lead Dioxide from Manufacture (0.115g Fraction)
Lead Dioxide vs Oxalic Acid : Hydrochloric Acid : Ethanol Reagent

4.00g Lead Dioxide
45g Ethanol Oxalic Acid Reagent
7ml Hydrochloric Acid Reagent
Chart Speed - 2/3 in/min.
Range - 1.15mv

Time, Minutes

FIGURE 9   Reactivity Curve of Lead Dioxide from Manufacturer 0 (1.55μ Fraction)
Lead Dioxide vs Oxalic Acid — Hydrochloric Acid — Ethanol Reagent

4.00g Lead Dioxide
45ml Ethanol Oxalic Acid
         Reagent
5ml Hydrochloric Acid
         Reagent
Chart Speed - 2/3 in./min.
Range = 1.25mv

FIGURE 10 Reactivity Curve of Lead Dioxide with Manufacturer 0 (1.7% Fractional)
Lead Dioxide vs Oxalic Acid — Hydrochloric Acid — Ethanol Reagent

4.00g Lead Dioxide
45ml Ethanol Oxalic Acid
    Reagent
5ml Hydrochloric Acid
    Reagent
Chart Speed - 1/3 in/min.
Range 1.25ev

Time, Minutes

FIGURE 11

Plot of Inflection Point of Temperature-Time
Curves Versus Reciprocal Particle Size for
Lead Dioxide Samples from Five Domestic
Manufacturers

Mfg. L = ●
Mfg. M = ▮
Mfg. N = ○
Mfg. O = ▢
Mfg. P = ▲

$\frac{\Delta T}{\Delta t}$ / t = ti in °C/min.

$\frac{1}{d} \times 10^6/m$

FIGURE 12   Plot of Inflection Point of Temperature-Time
Curves Versus Reciprocal Particle Size
Multiplied by Absolute Density for Lead
Dioxide Samples From Five Domestic Manufacturers

FIGURE 13 Numinco--Orr Pore Volume-- Surface Area Analyzer for the Determination of Specific Surface Area

FIGURE 14   A Pressure-Time Curve of
A Typical Mk 25 Mod 2
Starter Composition

$t\frac{1}{2}P_{max}$ = 2.75 secs = the time at which one half of the maximum pressure is attained.

θ = 64° = the slope of the curve at $t\frac{1}{2}P_{max}$.

tP_1 = 5 secs = time to the first peak, in the event there is more than one peak.

tP_{max} = 7.38 secs = time to the maximum pressure peak.

P_{max} = 8.5 psi = maximum pressure in psi.

P_c = 7.2 psi = pressure at which the normal cooling curve of the system is established.

ΔP = 1.3 psi = the difference between P_{max} and P_c.

ΔH = 375 cal/g = the heat of reaction. This value is not derived from the pressure-time curve, but from calorimetric determinations. It is included with the other data for convenient reference.

t_c = 10.5 secs = time until normal cooling curve is established.

50

FIGURE 15   Pressure-Time Curve of 2-3-5
            Starter Composition Made With
            Lead Dioxide from Sample L-1
            From Manufacturer L

51

FIGURE 16 Pressure-Time Curve of 2-3-5 Starter Composition Made With Lead Dioxide Sample L-2 From Manufacturer L

52

FIGURE 17 Pressure-Time Curve of 2-3-5
Starter Composition Made With
Lead-Dioxide Sample M-1
From Manufacturer M

Pressure, lbs/min²

17.5 —
15.0 —
12.5 —
10.0 —
7.5 —
5.0 —
2.5 —

Time, Seconds

0   2   4   6   8   10   12   14

53

FIGURE 18 Pressure-Time Curve of 2-3-5
           Starter Composition Made With
           Lead Dioxide Sample M-2
           From Manufacturer M

54

FIGURE 19 Pressure-Time Curve of 2-3-5 Starter Composition Made With Lead Dioxide Sample N-1 From Manufacturer L

55

FIGURE 20   Pressure-Time Curve of 2-3-5
             Starter Composition Made With
             Lead Dioxide Sample N-2
             From Manufacturer N

FIGURE 21 Pressure-Time Curve of 2-3-5
Starter Composition Made With
Lead Dioxide Sample N-3
From Manufacturer N

Time, seconds

FIGURE 22 Pressure-Time Curve of 2-3-5 Starter Composition Made With Lead Dioxide Sample N-4 From Manufacturer N

Time, seconds

Pressure, lbs/in^2

58

FIGURE 23   Pressure-Time Curve of 2-3-5
            Starter Composition Made With
            Lead Dioxide Sample O-1
            From Manufacturer O

Pressure, lbs/in^2

10   8   6   4   2   0

Time, seconds

59

FIGURE 24   Pressure-Time Curve of 2-3-5
Starter Composition Made With
Lead Dioxide Sample P-1
From Manufacturer P

FIGURE 25   Pressure-Time Curve Slope of
             2L-3C-5S Starter Composition
             Versus the Reciprocal Particle
             Size for 13 Lead Dioxide Samples
             from Six Domestic Manufacturers

Mfg. L = ●
Mfg. M = ▨
Mfg. N = ○
Mfg. O = ▢
Mfg. P = △
Mfg. Q = ▲

Tan θ

$\frac{1}{d}$ X 10^6/meter

FIGURE 26 Plot of Boron - Lead Dioxide Delay
Burning Rate Versus Reciprocal
Particle Size Multiplied by Absolute
Density for Five Lead Dioxide Sources

FIGURE 27   Plot of Boron - Lead Dioxide Delay
Burning Rate Versus Reciprocal
Particle Size Multiplied by Apparent
Density for Five Lead Dioxide Sources

Mfg. L = ●

Mfg. M = ■

Mfg. N = ○

Mfg. O = ▢

Mfg. P = △

Burn Rate gm/sec

$$\frac{1}{\rho_{apt}d} \times 10^4 \, cm^2/gm$$

63

FIGURE 28 Plot of Boron - Lead Dioxide Delay Burning Rate Versus Reciprocal Particle Size Multiplied by Absolute Density and Apparent Density for Five Lead Dioxide Sources

Burn Rate gm/sec

Mfg. L = ●
Mfg. M = ■
Mfg. N = ○
Mfg. O = □
Mfg. P = △

$$\frac{1}{d}\left(\frac{1}{\rho_{apt}} + \frac{1}{\rho_{abs}}\right) \times 10^4 \text{cm}^2/\text{gm}$$

FIGURE 29 Typical DTA Thermogram of
Lead Dioxide from Manufacturer L

FIGURE 30   Typical DTA Thermogram of
            Lead Dioxide from Manufacturer M

FIGURE 31   Typical DTA Thermogram of
             Lead Dioxide from Manufacturer N

FIGURE 32 Typical DTA Thermogram of
          Lead Dioxide from Manufacturer O

615

485
450

350

FIGURE 33   Typical DTA Thermogram of Lead
Dioxide from Manufacturer P

605

535

480

435

300

FIGURE 34   Typical DTA Thermogram of Lead
             Dioxide from Manufacturer Q

610

535

490

448

400

70

FIGURE 35 Typical DTA Thermogram of a 2:1 PbO_2:S Composition Using Lead Dioxide from Manufacturer L

FIGURE 36   Typical DTA Thermograms of 2:1 PbO_2:S
            Composition Using Lead Dioxide from
            Manufacturer M

Sample M-1   Sample M-2

FIGURE 37 Typical DTA Thermograms at 2:1 PbO_2:S Composition Using Lead Dioxide from Manufacturer N

IGN
225

200

150

Sample N-3

IGN
130

100

100

87

Sample N-4

FIGURE 38 Typical DTA Thermogram of 2:1 PbO_2:S
Composition Using Lead Dioxide from
Manufacturer O

IGN
310

167

115

Sample O

FIGURE 39   Typical DTA Thermograms of 2:1 PbO_2:S
Composition Using Lead Dioxide from
Manufacturer P

FIGURE 40   Typical DTA Thermogram of 2:1 PbO_2:S
             Composition Using Lead Dioxide from
             Manufacturer Q

Sample Q-1

FIGURE 41 Plot of Enthalpy vs. Percent of Silicon Fuel for Lead Dioxide Samples from Five Manufacturers.

FIGURE 42 Plot of Reaction Rate Constant, K,
Versus Surface Area for Lead Dioxide
Samples from Five Producers

Reaction Rate Constant, K, C°-m/min

Surface Area, m²/g   78

TABLE I

REACTIVITY DATA ON LEAD DIOXIDE SAMPLES FROM FIVE DOMESTIC
MANUFACTURERS

Lead Dioxide Source, Sample, Fraction	Average Particle Size, Microns	h_1 ΔT, °C	Time to Peak, Minutes	Slope at Inflection Point, °C/minute
Manufacturer L				
Sample 1				
Parent	1.73	16.88	39.3	0.69
Fraction 1	1.68	16.52	37.0	0.73
Fraction 2	2.0	16.2	49.0	0.62
Fraction 3	2.23	17.6	60.0	0.61
Manufacturer M				
Sample 1				
Parent	0.5	24.8	3.35	16.0
Fraction 1	0.59	23.04	3.74	10.2
Fraction 2	0.8	22.24	3.77	12.0
Manufacturer N				
Sample 3				
Parent	0.66	22.72	2.8	11.5
Fraction 1	0.64	23.6	3.2	15.3
Fraction 2	0.64	22.96	3.4	14.7
Manufacturer O				
Sample 1				
Parent	1.5	16.08	4.3	1.07
Fraction 1	1.2	17.32	17.0	2.06
Fraction 2	1.76	17.36	33.0	1.71
Fraction 3	1.55	17.92	29.0	2.06
Fraction 4	2.55	16.44	55.5	0.78
Manufacturer P				
Sample 1				
Parent	2.38	24.64	2.27	13.4
Fraction 1	1.85	22.72	3.3	14.0
Fraction 2	2.8	20.96	2.7	13.4

TABLE II

Values for the Reaction Rate Constant K

in the Equation $\left.\dfrac{\Delta T}{\Delta t}\right|_{t=ti} = K/d$

Manufacturer	K
L	1.40×10^{-6} °C-m/min.
M	7.75×10^{-6} °C-m/min.
N	7.70×10^{-6} °C-m/min.
O	2.10×10^{-6} °C-m/min.
P	26.90×10^{-6} °C-m/min.
Q	0.45×10^{-6} °C-m/min.

TABLE III

Comparison of Reactivity and Various Property
Values for 13 Lead Dioxide Samples
From Six Domestic Manufacturers

Lead Dioxide Source and Sample	Average Particle Diameter, Microns	Absolute Density, g/cc	Apparent Density, g/cc	Purity	Heat of Reaction, cal/g	Pressure time curve values			Delay Burning rates, g/sec	Reactivity, $K \times 10^{-5}$, °C - m/min.
						θ	P max	tp max		
Manufacturer L										
Sample #1	2.0	9.28	2.63	94.3	369.9	61	7.4	5.5	4.57	1.40
Sample #2	1.65		2.17	94.8	370.1	53	6.36	5.96	3.89	
Manufacturer M										
Sample #1	0.51	7.86	1.38	92.2	358.0	52	7.8	7.4	5.18	7.75
Sample #2	0.52		1.41	89.7	364.4	58	8.2	6.4	5.06	
Sample #3	0.6		1.44			61	8.0	6.0		
Manufacturer N										
Sample #1	0.32	6.82	1.43	89.4	360.1	50	8.7	9.1	4.85	
Sample #2	0.52	7.91	1.38	79.5	353.3	64	8.6	5.36	4.82	7.70
Sample #3	0.66	8.00	1.36	85.1	357.4	66	8.6	4.8	4.27	10.3
Sample #4	0.59	7.70	1.92	96.3	360.4	41	7.3	10.5	5.19	
Manufacturer O										
Sample #1	1.5	7.99	2.83	95.9	372.4	68	7.9	4.0	5.18	2.10
Manufacturer P										
Sample #1	2.38	7.92	2.26	95.9	360.7	59	7.5	6.2	2.97	26.9
Sample #2	1.20		1.68			63	7.1	5.1		
Manufacturer Q										
Sample #1	0.40	8.89	1.72		370.0	49	6.6	7.2	5.13	0.45
Sample #2	0.20					49	6.1	6.9	4.22	

TABLE IV

THE RELATIONSHIP BETWEEN THE AVERAGE PARTICLE DIAMETER, THE SURFACE AREA
AND THE REACTIVITY OF LEAD DIOXIDE FROM FIVE DOMESTIC MANUFACTURERS

Sample	Average Particle Diameter, Microns	Specific Surface Area, S_g, $m^2/9$	Computed Surface Area, $S = \frac{6v}{d}$ m^2/g	Reactivity Constant $K \times 10^{-6}$, °C-m/m
Manufacturer L	2.15	0.59 0.60	.30	1.40
Manufacturer M	0.60	4.94 4.94	1.27	7.75
Manufacturer N-3	0.60	4.38 4.33	1.25	7.70
Manufacturer O	.			.
Parent	1.85	0.96 0.97	.38	2.10
Fraction 1	2.55	0.66 0.67		
Fraction 2	1.76	0.94 1.00		
Fraction 3	1.55	1.14 1.09		
Fraction 4	1.20	1.52 1.49		
Manufacturer P	2.38	3.71 3.73	.32	26.9

TABLE V

Burning Characteristics of Boron-Lead Dioxide Delay Bodies

Lead Dioxide Sample Source	Average Particle Diameter, of PbO$_2$, g/cc	Apparent Density of PbO$_2$, g/cc	Absolute Density of PbO$_2$, g/cc	Weight of Composition per inch, grams	Average Burning Time, sec/inch	Burning Rate, g/sec
Manufacturer L						
Sample #1	2.0	2.63	9.28	3.85	0.843	4.57
Sample #2	1.65	2.17	-	3.85	0.989	3.89
Manufacturer M						
Sample #1	0.51	1.38	7.86	3.25	0.628	5.18
Sample #2	0.52	1.41	-	3.25	0.643	5.06
Sample #3	0.6	1.44	-	3.25	-	-
Manufacturer N						
Sample #1	0.32	1.43	6.82	3.00	0.619	4.85
Sample #2	0.52	1.38	7.91	3.25	0.676	4.82
Sample #3	0.66	1.36	8.00	3.25	0.761	4.27
Sample #4	0.59	1.92	7.70	3.25	0.626	5.19
Manufacturer O						
Sample #1	1.5	2.83	7.99	3.45	0.66	5.18
Manufacturer P						
Sample #1	2.38	2.26	7.92	3.386	1.140	2.97
Sample #2	1.20	1.68	-	3.386	-	-
Manufacturer Q						
Sample #1	0.60	1.72	8.89	-	-	-

TABLE VI

Differential Thermal Analysis Peaks for Lead Dioxide Samples From Six Domestic Manufacturers

Lead Dioxide Source and Sample	Endothermic Peaks	
	Run #1	Run #2
Manufacturer L		
Sample #1	465	465
	510	515
	645	630
Sample #2	475	480
	525	520
	645	640
Manufacturer M		
Sample #1	416	416
	460	460
	640	610
Sample #2	422	415
	460	455
	635	627
Sample #3	427	425
	465	460
	635	627
Manufacturer N		
Sample #1	412	400
	450	440
	610	615
Sample #2	410	420
	445	450
	615	615
Sample #3	420	427
	460	465
	625	620
Sample #4	435	420
	463	456
	507	610
	635	
Manufacturer O		
Sample #1	450	450
	485	485
	615	605
Manufacturer P		
Sample #1	465	435
	485	480
	525	535
	635	610
Sample #2	428	430
	478	480
	540	540
	605	590
Manufacturer Q		
Sample #1	448	448
	493	495
	537	533
	612	615
Sample #2	440	430
	490	485
	525	510
	627	615

TABLE VII

DIFFERENTIAL THERMAL ANALYSIS PEAKS FOR 2:1 LEAD DIOXIDE-SULFUR MIXTURE UTILIZING LEAD DIOXIDE SAMPLES FROM SIX DOMESTIC MANUFACTURERS

Lead Dioxide Source & Sample	Endothermic Peaks		Exothermic Peaks	
	Run #1	Run #2	Run #1	Run #2
Manufacturer L				
Sample #1	110	140	340*	335*
Sample #2	110	110	305*	307*
Manufacturer M				
Sample #1	115	145	125* ign. / 140	155* ign. / 148
Sample #2	110	115	202* ign. / 125	220* ign. / 147
Sample #3	98	110	200* ign.	200* ign.
Manufacturer N				
Sample #1	135	–	100 / 142* ign. / 130	90 / 135* ign. / 105
Sample #2	405* / 420	425*	140* / 130 / 200	135* ign. / 105
Sample #3	450	425*	265* / 92	275* ign. / 90
Sample #4	110	100	140* ign.	135* ign.
Manufacturer O				
Sample #1	115 / 203	115	165 / 210* ign.	170 / 210* ign.
Manufacturer P				
Sample #1	90	112	125 / 312	145 / 310 / 100 / 165
Sample #2	440*	425*	150* ign.	275* ign.
Manufacturer Q				
Sample #1	97 / 415 / 443	135	125 / 275*	110 / 150 / 180 / 293* ign.
Sample #2	125 / 450*	112 / 435*	97 / 150 / 165 / 230 / 310*	92 / 145 / 155 / 225 / 305*

TABLE VIII

CALORIFIC VALUES FOR THE HEATS OF REACTION OF DIFFERENT RATIOS OF
LEAD DIOXIDE AND SILICON

Ratio of Pbo$_2$ to S:	Heat of Reaction in cal/g				
	Manuf L	Manuf M	Manuf N	Manuf O	Manuf P
9.5 : 0.5				301.1 302.0	
9.0 : 1.0	483.6 480.3	460.8 458.1	446.1 443.3	440.5 441.3	485.4 488.9
8.7 : 1.3				493.1 489.7	
8.5 : 1.5				501.1 500.0	
8.0 : 2.0	483.2 490.4	477.9 468.0	484.9 486.9		506.7 505.7
7.5 : 2.5				441.0 443.0	
7.0 : 3.0	423.7 421.4	395.8 413.2	422.0 423.0		444.6 450.4
6.0 : 4.0	353.9 347.0	341.5 355.6	354.5 359.6		364.8 362.7
5.0 : 5.0	295.8 299.0	291.0 288.9	301.1 297.5	292.0 291.7	311.3 309.8
4.0 : 6.0	241.9 240.1	233.3 231.2	233.3		246.2 230.2
3.0 : 7.0	166.2 172.2	155.9 156.7	183.4 177.7	179.8 178.0	165.8 162.2

TABLE IX

CHEMICAL ANALYSIS OF ELEVEN LEAD DIOXIDE SAMPLES FROM SIX DOMESTIC MANUFACTURERS

Manufacturer and sample	Purity o/o PbO_2	Insoluble in $H_2O_2-HNO_3$	Soluble in H_2O	Pb, o/o	Theoretical PbO_2 based on o/o Pb
Manufacturer L					
Sample 1	94.3	0.05	1.2	86.0	99.2
Sample 2	94.8	0.08	0.0	84.2	97.2
Manufacturer M					
Sample 1	92.2	0.01	0.74	84.6	97.7
Sample 2	89.7	0.06	0.0	84.8	97.8
Manufacturer N					
Sample 1	89.4	0.05	0.0	83.9	97.0
Sample 2	79.5	0.13	0.0	84.9	97.9
Sample 3	85.1	0.04	0.39	85.2	98.3
Sample 4	96.3	0.01	0.13	85.8	99.1
Manufacturer O					
Sample 1	95.9	0.0	0.35	85.5	98.7
Manufacturer P					
Sample 1	95.9	0.0	1.4	86.1	99.3
Manufacturer Q					
Sample 1	98.1	0.0	0.10	85.9	98.6

TABLE X

d - SPACINGS OBTAINED FROM X-RAY DIFFRACTION PATTERNS OF LEAD DIOXIDE SAMPLES FROM FIVE DOMESTIC MANUFACTURERS

Manuf L	Manuf M	Manuf N	Manuf O	Manuf P
3.50	3.50	3.48	3.50	3.49
-	-	3.12	3.14	3.12
2.79	2.79	2.78	2.79	2.79
2.47	2.47	2.47	2.47	2.47
1.85	1.85	1.85	1.85	1.85
1.75	1.75	1.74	1.75	1.75
1.69	1.69	1.69	1.69	1.69
1.56	1.56	1.56	1.57	1.57
1.52	1.52	1.52	1.52	1.52
1.48	1.48	1.48	1.48	1.48
1.40	1.40	1.40	1.40	1.40
1.27	1.27	1.27	1.27	1.27
1.23	1.23	1.24	1.24	-
1.21	1.21	1.21	1.22	1.21
1.17	1.17	1.16	1.17	1.17
1.15	1.15	1.15	1.15	-
1.13	1.13	1.13	1.13	
		1.11	1.11	
		1.10	1.10	

ASTM POWDER DIFFRACTION DATA
CARDS FOR LEAD DIOXIDE

8-185

d	3.50	2.80	1.46	3.50	PbO_2					
I/I_1	100	100	100	100	Lead Dioxide		Plattnerite			

Rad. CuKα λ 1.542   Filter Ni   Dia. 6cm
Cut off 16 I/I_1 Visual estimate
Ref. G. F. Claringbull, British Museum

Sys. Tetragonal   S.G. D_{4h}^{14} - $P4_2/mnm$
a₀ 4.941 b₀   c₀ 3.374 A   C 0.683
α   β   γ   Z 2   Dx 9.43
Ref. Darbyshire, J.Chem.Soc. 211 (1932)

εα   nωβ 2.30(Li)   εγ   Sign -
2V   D 9.42   mp   Color Jet to brownish black
Ref. Dε,Vε

Sample from Leadville, Leadenshire (BM 56917)
D.T. 312° (760mm); Sol. in HCl. Analysis in Min. Mag. 7
33 (1886).

Replaces 1-0473

d Å	I/I_1	hkl	d Å	I/I_1	hkl
3.50	35	110	1.001	20	213
2.80	100	101	0.975	40	440
2.49	70	200	.942	40	332
2.21	10	210	.942	70	431,402
1.959	100	211	.933	20	411
1.754	40	220	.929	40	
1.693	40	002			
1.569	40	310			
1.527	10	112			
1.464	70	301			
1.399	50	202			
1.276	70	321			
1.240	20	400			
1.220	40	222			
1.179	20	330			
1.152	70	312			
1.134	70	411			
1.110	40	420			
1.102	40	341			
1.005	60	431			

11-548

d	3.90	2.44	2.79	2.90	β-PbO_2 (corrosion product)					
I/I_1	100+	90	40	100+	Beta Lead Dioxide					

Rad. λ   Filter   Dia.
Cut off I/I_1 Visual
Ref. Burbank, J. Electrochem. Soc. 104 693 (1957)

Sys. Tetragonal   S.G. $P4_2/mnm$ (136)
a₀ 4.99 b₀   c₀ 3.37 A   C 0.685
α   β   γ   Z   Dx 9.63
Ref. Ibid.   D 4.42

Sample is an anodic corrosion product of Pb and was
obtained in acid medium at elevated potentials.

d Å	I/I_1	hkl	d Å	I/I_1	hkl
3.90	100+	110			
2.79	80	101			
2.44	90	200			
1.95	30	211			
1.73	30	220			
1.69	30	002			
1.556	30	310			
1.519	30	112			
1.446	30	301			
1.347	30	202			
1.273	30	321			
1.236	30	400			
1.214	30	222			
1.152	30	312			

11-549

d	3.12	2.74	2.43	3.83	α-PbO_2					
I/I_1	100	70	70	12	Alpha Lead Dioxide					

Rad. CuKα λ 1.5418   Filter Ni   Dia. 346 mm
Cut off 4.31 I/I_1 G.C. diffractometer
Ref. R.A. Gross, Australian Defence Scientific Service,
Defence Standards Laboratories, Dept. of Supply, Melbourne
Australia

Sys. Orthorhombic   S.G. Pbcn (60)
a₀ 4.938 b₀ 5.939 c₀ 5.486 A 0.8316 C 0.9237
α   β   γ   Z 4   Dx 9.875
Ref. P. Rooksby, and B.D. Cullen, J.Electrochem. Soc. 104
404-413 (1957)

Non-anal.: Reflections tried from Zaslavsky et al.,
Doklady Akad. Nauk SSSR 75 559 (1950).
D.S.L. sample prepared by method of S.E. Clarke,
J. Electrodepositing Tech. Soc. 12 26 (1937).
Positions and Cullen give a .188 at 3.53 A which probably
arises from β-PbO_2.

Replaces 10-518

d Å	I/I_1	hkl	d Å	I/I_1	hkl
3.83	12	110			
3.12	100	111			
2.97	15	020			
2.74	70	002			
2.43	70	021			
2.46	30	200			
2.23	6	112			
2.02	6	022			
1.89	30	220			
1.84	45	130,202			
1.79	30	221			
1.64	15	113			
1.54	17	222,023			
1.53	30	311,132			
1.47	30	041,312			
1.37	15	312			
1.31	15	223			
1.28	20	330			
1.26	30	341,400			
1.10	8	304,313			

99

APPENDIX II

KEY WORDS

Lead Dioxide

Structural Variations

Chemical Reactivity

Density

Reactivity of Lead Dioxide

Crystallinity

X-Ray Diffraction Patterns

Fractionations

Reaction Rate

Kinetics

Surface Area

Rate Calorimeter

Delay Burning Rate

DOCUMENT CONTROL DATA - R&D		
(Security classification of title, body of abstract and indexing annotation must be entered when the overall report is classified)		

1 ORIGINATING ACTIVITY (Corporate author)	2a. REPORT SECURITY CLASSIFICATION
Research and Development Department	UNCLASSIFIED
U. S. Naval Ammunition Depot	2b GROUP
Crane, Indiana	

3 REPORT TITLE

A Preliminary Investigation of the Reactivity of Lead Dioxide

4. DESCRIPTIVE NOTES (Type of report and inclusive dates)

5 AUTHOR(S) (Last name, first name, initial)

RIPLEY, WILLIAM L.   and   LIPSCOMB, CHARLES A.

6. REPORT DATE	7a. TOTAL NO. OF PAGES	7b. NO. OF REFS
13 June 1968	90	

8a CONTRACT OR GRANT NO.	9a ORIGINATOR'S REPORT NUMBER(S)
b. PROJECT NO. Air Task A 35-532-022/323-1/F008-17-02	RDTR No. 114
c. Work Unit 6	9b OTHER REPORT NO(S) (Any other numbers that may be assigned this report)
d.	

10. AVAILABILITY/LIMITATION NOTICES

Distribution of this document is unlimited.

11. SUPPLEMENTARY NOTES	12. SPONSORING MILITARY ACTIVITY
	Naval Air Systems Command

13 ABSTRACT

A study is made of the performance characteristics of lead dioxide specimens from five U. S. manufacturers. Reactivity data is obtained using temperature-time curves, pressure-time curves, and burning rate of delay bodies. The relationship of chemical and physical properties of lead dioxide to its performance in the various tests, and the relationship of the various performance tests to each other, are considered.

DD FORM 1473   0101-807-6800

14 KEY WORDS	LINK A		LINK B		LINK C	
	ROLE	WT	ROLE	WT	ROLE	WT
Lead Dioxide						
Structural Variations						
Chemical Reactivity					•	•
Density						
Reactivity of Lead Dioxide		ı				
Crystallinity				∕		∕
X-Ray Diffraction Patterns	∕					
Fractionations						
Reaction Rate						
Kinetics						
Surface Area						
Rate Calorimeter						
Delay Burning Rate			•			
William L. Ripley						

INSTRUCTIONS

1. ORIGINATING ACTIVITY: Enter the name and address of the contractor, subcontractor, grantee, Department of Defense activity or other organization (corporate author) issuing the report.

2a. REPORT SECURITY CLASSIFICATION: Enter the overall security classification of the report. Indicate whether "Restricted Data" is included. Marking is to be in accordance with appropriate security regulations.

2b. GROUP: Automatic downgrading is specified in DoD Directive 5200.10 and Armed Forces Industrial Manual. Enter the group number. Also, when applicable, show that optional markings have been used for Group 3 and Group 4 as authorized.

3. REPORT TITLE: Enter the complete report title in all capital letters. Titles in all cases should be unclassified. If a meaningful title cannot be selected without classification, show title classification in all capitals in parenthesis immediately following the title.

4. DESCRIPTIVE NOTES: If appropriate, enter the type of report, e.g., interim, progress, summary, annual, or final. Give the inclusive dates when a specific reporting period is covered.

5. AUTHOR(S): Enter the name(s) of author(s) as shown on or in the report. Enter last name, first name, middle initial. If military, show rank and branch of service. The name of the principal author is an absolute minimum requirement.

6. REPORT DATE: Enter the date of the report as day, month, year; or month, year. If more than one date appears on the report, use date of publication.

7a. TOTAL NUMBER OF PAGES: The total page count should follow normal pagination procedures, i.e., enter the number of pages containing information.

7b. NUMBER OF REFERENCES: Enter the total number of references cited in the report.

8a. CONTRACT OR GRANT NUMBER: If appropriate, enter the applicable number of the contract or grant under which the report was written.

8b, 8c, & 8d. PROJECT NUMBER: Enter the appropriate military department identification, such as project number, subproject number, system numbers, task number, etc.

9a. ORIGINATOR'S REPORT NUMBER(S): Enter the official report number by which the document will be identified and controlled by the originating activity. This number must be unique to this report.

9b. OTHER REPORT NUMBER(S): If the report has been assigned any other report numbers (either by the originator or by the sponsor), also enter this number(s).

10. AVAILABILITY/LIMITATION NOTICES: Enter any limitations on further dissemination of the report, other than those imposed by security classification, using standard statements such as:

(1) "Qualified requesters may obtain copies of this report from DDC."

(2) "Foreign announcement and dissemination of this report by DDC is not authorized."

(3) "U. S. Government agencies may obtain copies of this report directly from DDC. Other qualified DDC users shall request through

_____."

(4) "U. S. military agencies may obtain copies of this report directly from DDC. Other qualified users shall request through

_____."

(5) "All distribution of this report is controlled. Qualified DDC users shall request through

_____."

If the report has been furnished to the Office of Technical Services, Department of Commerce, for sale to the public, indicate this fact and enter the price, if known.

11. SUPPLEMENTARY NOTES: Use for additional explanatory notes.

12. SPONSORING MILITARY ACTIVITY: Enter the name of the departmental project office or laboratory sponsoring (paying for) the research and development. Include address.

13. ABSTRACT: Enter an abstract giving a brief and factual summary of the document indicative of the report, even though it may also appear elsewhere in the body of the technical report. If additional space is required, a continuation sheet shall be attached.

It is highly desirable that the abstract of classified reports be unclassified. Each paragraph of the abstract shall end with an indication of the military security classification of the information in the paragraph, represented as (TS), (S), (C), or (U).

There is no limitation on the length of the abstract. However, the suggested length is from 150 to 225 words.

14. KEY WORDS: Key words are technically meaningful terms or short phrases that characterize a report and may be used as index entries for cataloging the report. Key words must be selected so that no security classification is required. Identifiers, such as equipment model designation, trade name, military project code name, geographic location, may be used as key words but will be followed by an indication of technical context. The assignment of links, roles, and weights is optional.